

CSP SPORTS & REC

A division of Child Safe Products. Inc.

FAST TRACK™ 100

FULL DEPTH SYSTEM

A. PRODUCT

FAST TRACK™ 100 is a porous paved-in-place synthetic sport surface comprised of polyurethane binder and 100% EPDM rubber granules.

B. MATERIALS

Primer

Polyurethane-based primers especially formulated to be compatible with the base and track surfacing materials.

EPDM Granules

The rubber granules for the base mat shall be 100% EPDM rubber, processed and chopped to 1-3 mm size, containing 0% dust.

Polyurethane Binder

Binder for rubber mat shall be an aromatic-based, mono-component. The binding agent shall not have a free TDI monomer level above 0.2%. The binding agent must be specially formulated for compatibility with EPDM rubber.

Line Paint

The line marking paint shall be polyurethane-based paint, specifically manufactured to be compatible with polyurethane synthetic surfaces.

C. EXECUTION

Curing

Before application of the synthetic surface can begin, the asphalt should be cured for at least 14 days; and a concrete base a minimum of 28 days.

Cleaning

The area to be surfaced shall be clean and free of any loose or foreign particles (dirt, oil,

etc.) prior to commencement of the work. The surface is usually cleaned by use of a power blower and/or high-pressure washer.

Priming

The primer shall be spray-applied in accordance with the manufacturer's specifications. Only those areas that can be installed the same day should be primed.

Composition of Mix shall be as follows:

- EPDM Rubber Granules 100 %
- Aromatic Binder 20% of total rubber weight

Surface Installation

The black rubber and polyurethane binding agent are blended together in a suitable mixer for a period of 2-3 minutes. The blended materials are then spread onto the asphalt/concrete base by means of a mechanical tandem leveler at a rate of 16 to 16.5 pounds per square yard. The tandem leveler shall have a heated oscillating screed bar to obtain both smoothness and compaction. The heated screed bar normally works at a temperature of 158 - 176 Degrees F.

The laying procedure shall be bay-to-bay and limiting the length of the passes so as not to have any cold (cured) joints between the bays. At the beginning of each new day's work the traverse joint from the previous day's work shall be tack coated to ensure a good bond. Any small irregularities remaining in the surface after the tandem leveler has passed may be removed using a light polyethylene or Teflon roller or hand trowel.

The surface hardens through the reaction of the binding agent with humidity. The speed of the reaction depends on temperature and relative humidity. Usually the surface may be walked upon the next day.

Line Markings

All line and event markings shall be applied by experienced personnel utilizing polyurethane-based paint compatible with the synthetic track surfacing. All marking dimensions will be in accordance with the specifications issued by the appropriate sanctioning or governing body such as IAAF, NCAA, NFSHSA, etc.

D. PERFORMANCE STANDARDS

Physical Properties (ASTM/IAAF)

Colors: As per spec

Thickness: (1/2") 12-13 mm or as specified by architect/engineer or owner

Density: 0.75 - 0.78

ASTM D-412 Elongation at break: Approx 95% as per spec

ASTM D-412 Tensile Strength: 0.70 N/mm2@ 70F

ASTM D-395 Compression Set Recovery: 90% to 95% @ 70F over 24-hour period ASTM D-501 Abrasion Resistance: 0.25 – 0.425 grams loss after 1000 cycles

ASTM D-822 Chalking: No change > 1000 hours

ASTM D-1984 Coefficient of Friction: Dry: 0.70 to 0.75 Wet: 0.80 – 0.95

ASTM D-2632 Resilience: 37 – 44% ASTM D-624 Tear Resistance: 60 - 75 PSI

E. INSTALLER

FAST TRACK™ 100 shall be installed only by factory certified full-time employees.

F. WARRANTY

FAST TRACK™ 100 is warranted against defects in workmanship, labor and materials under normal use and service. The warranty excludes damage or defects caused by improper design or engineering, by an inadequate or defective base, by normal wear and tear, vandalism, abuse, neglect or lack of maintenance.

G. MANUFACTURER

FAST TRACK™ 100 as manufactured by CHILD SAFE PRODUCTS, INC. 550 Main Street
Westbury, NY 11590
516-848-7773

E-Mail: Joe@CSPsportsandrec.com Website: www.cspsportsandrec.com



End of Section

NOTICE: These specifications are merely guides for use by Landscape Architects, Engineers and Contractors. It is hoped that these specifications will be of particular value to those who do no not have detail knowledge of synthetic running tracks and that it will aid in maintaining high construction standards. CHILD SAFE PRODUCTS, its agents and employees do not warrant the specifications as proper under all conditions.

